

16 April 2004

World Intellectual Property Organization

10/541032

PCT Administration Division

JC17 Rec'd PCT/PTO 28 JUN 2005

34 Chemin des Colombettes

5 1211 GENEVA 20

SWITZERLAND

"Amendment of the Claim under Article 19(1) (Rule 46)."

10 Re: International Application No. PCT/JP2003/016640

Applicant: JSR CORPORATION et al

Agent: WAKI Misao

International Filing Date: 24 December 2003

15 Dear Sir.

The applicant, who received the International Search Report relating the above-identified International Application transmitted on 5 March 2004, hereby files amendment under Article 19(1) as in the attached sheets.

Further, the applicant hereby does not cancel any sheets. Thus claim 1 is amended, claims 2-5 are retained unchanged, claim 6 is cancelled, and claim 7 to claim 10 are retained unchanged with the exception of renumbering claim Numbers.

The applicant also files as attached herewith a brief statement explaining the amendment and indicating any impact that amendment therein might have on the description.

Very truly yours,

  
WAKI Misao

5

Attachment:

(1) Amendment under Article 19(1)

1 sheet

(2) Brief statement

1 sheet

10


1. A radiation-sensitive resin composition comprising

an acid-labile group-containing resin which is insoluble or scarcely soluble in

5 alkali, but becomes alkali soluble by the action of an acid, and

a photoacid generator,

wherein the acid-labile group-containing resin comprises a recurring unit of the following formula (1) and has a ratio of a weight average molecular weight to a number average molecular weight (weight average molecular weight/number average molecular weight) of smaller than 1.5 and is polymerized with a living radical polymerization  
10 initiator,




(1)

wherein  $\text{R}^1$  individually represents a hydrogen atom, methyl group, trifluoromethyl group, or hydroxymethyl group and  $\text{R}^2$  individually represents a monovalent alicyclic


15 hydrocarbon group having 4-20 carbon atoms or a derivative thereof, or a linear or branched alkyl group having 1-4 carbon atoms, in which at least one of  $\text{R}^2$  groups is a monovalent alicyclic hydrocarbon group or a derivative thereof, or any two of  $\text{R}^2$  groups form a divalent alicyclic hydrocarbon group having 4-20 carbon atoms or a derivative thereof in combination with the carbon atom to which the two  $\text{R}^2$  groups bond, with the  
20 remaining  $\text{R}^2$  group being a linear or branched alkyl group having 1-4 carbon atoms or a monovalent alicyclic hydrocarbon group having 4-20 carbon atoms or a derivative

thereof.


2. The radiation-sensitive resin composition of claim 1, wherein the acid-labile group-containing resin comprises a recurring unit of the formula (1) and at least one  
5 recurring unit selected from the group consisting of the recurring units of the following formulas (2)-(7),




(2)




(3)




(4)



(5)



(6)



(7)

wherein R¹ individually represents a hydrogen atom, methyl group, trifluoromethyl group, or hydroxymethyl group, A represents a single bond, a substituted or unsubstituted, linear  
10 or branched alkylene group having 1-6 carbon atoms, a mono- or dialkylene glycol group, or an alkylene ester group, B represents a single bond, a substituted or unsubstituted alkylene group having 1-3 carbon atoms, an alkyloxy group, or an oxygen atom, E

represents a single bond or a divalent alkyl group having 1-3 carbon atoms,  $R^3$  individually represents a hydroxyl group, cyano group, carboxyl group,  $-COOR^5$ , or  $-Y-R^6$ , wherein  $R^5$  represents a hydrogen atom, a linear or a branched alkyl group having 1-4 carbon atoms, or an alicyclic alkyl group having 3-20 carbon atoms, Y individually represents a single bond or a divalent alkylene group having 1-3 carbon atoms,  $R^6$  individually represents a hydrogen atom, hydroxyl group, cyano group, or  $-COOR^7$ , provided that at least one  $R^3$  group is not a hydrogen atom,  $R^7$  represents a hydrogen atom, a linear or branched alkyl group having 1-4 carbon atoms, or an alicyclic alkyl group having 3-20 carbon atoms, G represents a single bond, a linear or branched alkylene group having 1-6 carbon atoms, an alicyclic hydrocarbon group having 4-20 carbon atoms, an alkylene glycol group, or an alkylene ester group, J, L, N, and M individually represent a single bond, a substituted or unsubstituted, linear, branched, or cyclic alkylene group having 1-20 carbon atoms, an alkylene glycol group, or an alkylene ester group, p is 0 or 1,  $R^4$  represents a hydrogen atom, a linear or branched alkyl group having 1-4 carbon atoms, an alkoxy group, a hydroxyalkyl group, or a divalent alicyclic hydrocarbon group having 3-20 carbon atoms or a derivative thereof, and q is 1 or 2.

3. The radiation-sensitive resin composition of claim 2, wherein the acid-labile group-containing resin comprises the recurring unit of the formula (2), at least one of the recurring units of the formula (2) to (7).

4. The radiation-sensitive resin composition according to either claim 2 or claim 3, wherein the content of the recurring unit (1) is 15-70 mol% of the total amount of the recurring units.


5. The radiation-sensitive resin composition according to claim 4, wherein the acid-labile group-containing resin is a polymer produced by random polymerization of

the recurring units which form the resin.

6. The radiation-sensitive resin composition according to claim 1, wherein the living radical polymerization initiator is a mixture of a transition metal complex, an

5 organic halide, and a Lewis acid or an amine.

7. The radiation-sensitive resin composition according to claim 1, wherein the living radical polymerization initiator is a compound of the following formula (8),



(8)

10 wherein R' represents an alkyl group or an aryl group having 1-15 carbon atoms which may contain an ester group, ether group, amino group, or amide group; Y represents a single bond, oxygen atom, nitrogen atom, or sulfur atom; and R'' represents an alkyl group or an aryl group having 1-15 carbon atoms which may contain an ester group, ether group, or amino group.

15

8. The radiation-sensitive resin composition according to either claim 6 or claim 7, wherein terminal processing of the living radical polymerization initiator is conducted using a heat radical generator.

20

9. The radiation-sensitive resin composition according to claim 1, wherein the photoacid generator comprises at least one compound selected from the group consisting of a triphenylsulfonium salt compound, a 4-cyclohexylphenyldiphenylsulfonium salt compound, a 4-t-butylphenyldiphenylsulfonium salt compound, and a tri(4-t-butylphenyl)sulfonium salt compound.

10. The radiation-sensitive resin composition according to claim 1, further comprising a nitrogen-containing organic compound as an acid diffusion controller.